

# ANDEROL 5460 XEP

Synthetic Gear and Bearing Lubricant

www.Oil18.ru : 902313@inbox.ru : tel (3412) 902-313

Product Data Sheet



**ANDEROL 5460 XEP** is a synthetic based, high performing gear lubricant to be used in industrial equipment. It was formulated to withstand heavy loads and severe conditions resulting in very good micro pitting resistance. The PAO based product gives superior advantages to the mineral oil based products, especially with regards to low pour point, oxidation stability and energy consumption.

**ANDEROL 5000 XEP** range is available in the grades ISO VG 150, 220, 320, 460, 680 and 1000.

Meets or exceeds the requirements of:

- ANSI/AGMA 9005 (table 3)
- AISE 224 (formerly USS 224)
- DIN 51.517
- Cincinnati Machine P-35

## ADVANTAGES / BENEFITS

- Excellent oxidation and thermal stability
- Wide operating temperature range
- Lower maintenance costs
- Excellent load carrying ability
- Extended lubricant life
- Improved cleanliness
- Excellent anti wear & EP properties
- Very good rust and copper corrosion prevention
- Compatible with petroleum oils, therefore allowing minimal effort to changeover

## COMPATIBILITY

The following seals, paints and plastics are recommended for use in contact with Anderol Company Synthetic Lubricants. Materials not recommended are also shown. For more information on other materials see our 'Compatibility Guide'.

### RECOMMENDED :

Viton, High Nitrile Buna N, Teflon, Epoxy Paint, Oil-Resistant Alkyd, Nylon, Delrin, Celcon, PBT

### NOT RECOMMENDED:

Neoprene, SBR Rubber, Low Nitrile Buna N, Acrylic Paint, Lacquer, Polystyrene, PVC, ABS

## APPLICATION

- Particularly suited for gear applications exposed to extreme service conditions
- All types of enclosed gear drives
- Bearings, including plain rolling elements and antifriction types
- Enclosed gear cases and speed reducers

## APPROVALS

- Flender
- Rossi Motoriduttori
- Kumera Drives

PROPERTIES	TEST METHOD	ANDEROL 5460 XEP
Appearance @ 20°C	visual	Clear Yellow Liquid
Viscosity @ 40°C, cSt	ASTM D-445	420.2
Viscosity @ 100°C, cSt	ASTM D-445	42.4
Viscosity Index	ASTM D-2270	154
Density @ 15°C, kg/l	ASTM D-1298	0.908
Total Acid Number, mg KOH/g	ASTM D-664	0.5
Flash Point, °C	ASTM D-92	250
Pour Point, °C	ASTM D-97	-42
Foam , Sequence I,II ml	ASTM-892	20
Micro pitting Resistance Test	FVA,54/11	High
FZG Gear Test, Pass Stage	DIN/ISO 14635-1	14
FE-8 Industrial Gear requirements	DIN 51819 T1-T3	
* Bearing Lubrication Test J1 (FAG Step I)		Pass
* Bearing Lubrication Test J2 (FAG Step II)		Pass
FAG Wind Power requirements		
* Wind power Level 3 Test L11 (FAG Step III)		Pass
* Oil suitability for Wind Energy Plant Applications (FAG Step IV)		Pass
Four Ball Wear, 1200 rpm, 75°C, 40 kg	ASTM D-4172	0.5
Four Ball Weld, kg	ASTM D-2783	250

FOR MORE INFORMATION PLEASE REFER TO THE RELEVANT MATERIAL SAFETY DATA SHEET

## APPROVALS / REGISTRATIONS



### ANDEROL BV

Punterweg 21 A  
6222 NW MAASTRICHT  
The NETHERLANDS

Tel No.: +31 (0)43 352 41 90  
Fax No.: +31 (0)43 352 41 99  
www.anderol-europe.com



This information is furnished without warranty, representation, inducement, or license of any kind except that it is accurate to the best of OUR knowledge or obtained from sources believed by ANDEROL to be accurate. ANDEROL does not assume any legal responsibility for use of reliance upon it. Only Chemists or chemically qualified lab technicians should carry out tests. Before using any chemicals, read its label and Material Safety Data Sheet.