



ANDEROL 750 is an ISO 150 synthetic diester based compressor lubricant specifically designed to provide long-term lubrication in air and process gas compressors.

ANDEROL 750 meets or exceeds the following specifications:

DIN 51506

ADVANTAGES / BENEFITS

No metal additives to interfere with catalytic processes

- Fewer oil changes
- Reduces compressor maintenance
- Greatly reduces fire and explosion hazard
- Separates water condensate rapidly
- Lower oil consumption
- Eliminates lacquering and deposits
- Reduces energy consumption

COMPATIBILITY

The following seals, paints and plastics are recommended for use in contact with Anderol synthetic lubricants. Materials not recommended are also shown. For more information on other materials see our 'Compatibility Guide'.

RECOMMENDED:

Viton, High Nitrile Buna N, Teflon, Epoxy Paint, Oil-Resistant Alkyd, Nylon, Delrin, Celcon, PBT

NOT RECOMMENDED:

Neoprene, SBR Rubber, Low Nitrile Buna N, Acrylic Paint, Lacquer, Polystyrene, PVC, ABS

APPLICATION

- Air
- Butadiene
- Carbon Monoxide
- Carbon Dioxide(dry)
- Ethylene
- Helium
- Hydrogen
- Natural gas
- Methane
- Nitrogen
- Propane

Cylinder and crankcase lubrication for reciprocating compressors, vane compressors and vacuum pumps.

Nominal Operating Range -15°C to 230 °C

PROPERTIES	TEST METHOD	ANDEROL 750
Appearance @ 20°C	visual	Clear Yellow Liquid
Viscosity @ 40°C, cSt	ASTM D-445	164.6
Viscosity @ 100°C, cSt	ASTM D-445	13.4
Viscosity Index	ASTM D-2270	69
Density @ 15°C, kg/l	ASTM D-1298	0.947
Total Acid Number, mg KOH/g	ASTM D-664	0.06
Flash Point, °C	ASTM D-92	246
Pour Point, °C	ASTM D-97	-33
Demulsibility @ 82°C,min	ASTM D-1401	15

FOR MORE INFORMATION PLEASE REFER TO THE RELEVANT MATERIAL SAFETY DATA SHEET

APPROVALS / REGISTRATIONS



ANDEROL BV

Punterweg 21 A
6222 NW MAASTRICHT
The NETHERLANDS

Tel No.: +31 (0)43 352 41 90
Fax No.: +31 (0)43 352 41 99
www.anderol-europe.com