



**ANDEROL 7220 FG** is a high performance product, designed primarily for industrial worm gear applications in the food & beverage industry. It may also be considered as a general purpose gear lubricant or to lubricate chains and ways. This fluid is a synthetic Polyalkylene Glycol (PAG) based fluid that provides excellent thermal and oxidative stability, load carrying ability and sludge-free operation over a wide temperature range. The PAG base stock is enhanced with a special mixture of additives providing thermal oxidation stability and anti wear performance.

**ANDEROL 7220 FG** is NSF/H1 and InS/H1 registered. ANDEROL Food Grade Lubricants meet the requirement of the FDA regulation 21 CFR 178.3570.

### ADVANTAGES / BENEFITS

- Long life, fewer oil changes
- High water tolerance
- Very good heat dissipation
- Improved thermal stability
- Increased oxidative stability
- Extends equipment life
- High and low temperature operations
- Excellent corrosion inhibition
- Reduced volatility
- No sludge formation

### COMPATIBILITY

**ANDEROL 7220 FG** is PAG based, therefore thorough cleaning is recommended when mixing with any other chemistries, such as petroleum based (mineral oils) and/or PAO (Polyalphaolefins).

When changing over from a conventional mineral oil care should be taken to minimize contamination caused by decomposition material from the previous lubricant. Thorough cleaning with an ester followed by a light petroleum solvent is advisable.

### APPLICATION

- Worm gears
- Chains and ways, including high water containing applications.

They can also be used in:

- Low speed gear sets
- Bearings
- Circulation systems
- Almost all gear sets requiring an ISO 150 or 220 VG oil.

PROPERTIES	TEST METHOD	ANDEROL 7220 FG
Appearance @ 20°C	visual	Clear liquid
Viscosity @ 40°C, cSt	ASTM D-445	216.0
Viscosity @ 100°C, cSt	ASTM D-445	34.3
Viscosity Index	ASTM D-2270	207
Density @ 15°C, kg/l	ASTM D-1298	0.9996
Total Acid Number, mg KOH/g	ASTM D-664	1.57
Flash Point, COC, °C	ASTM D-92	274
Pour Point, °C	ASTM D-97	- 42
Four ball Wear, 1200 rpm, 75°C, 40kg	ASTM D-4172	0.32
Four Ball Weld, kg	ASTM D-2783	200
Copper Corrosion	ASTM D-130	1a
Steel corrosion, Sea water	ASTM D665B	Pass
FZG A/8.3/90 , failure load stage	ISO 14635-1	14
Oxidation characteristics of extreme pressure lubricant, 121°C, 312 HRS, numbers of precipitation	ASTM 2893	0
Air release at 75°C (min)	ASTM D3427	8.2

FOR MORE INFORMATION PLEASE REFER TO THE RELEVANT MATERIAL SAFETY DATA SHEET

### APPROVALS / REGISTRATIONS



**ANDEROL BV**  
 Punterweg 21 A  
 6222 NW MAASTRICHT  
 The NETHERLANDS  
 Tel No.: +31 (0)43 352 41 90  
 Fax No.: +31 (0)43 352 41 99  
 www.anderol-europe.com

